

DURaflex[®]

DECO PLUS

FIBER CEMENT BOARD

BEAUTIFUL | COOL | DURABLE


SAINT-GOBAIN

TECHNICAL INFORMATION


CHARACTERISTICS	VALUE	TEST METHOD
Density	1.25 - 1.45 g/cm ³	ASTM C1185-08
Material Classification	Non combustible	BS 476-Pt 4: 1970
Fire Propagation	Performance index & sub-indeces = 0,0,0,0.	BS 476-Pt 6: 1989
Surface Spread of Flame	Class 1	BS 476-Pt 7: 1997
Moisture Content	8 - 10 %	ASTM C1185-08
Moisture Movement	0.01 - 0.07 %	ASTM C1185-08
Water Absorption	< 35 %	ASTM C1185-08
Average Flexural Strength	14 - 16 MPa	ASTM C1185-08
Impact Strength	10 - 14 J	JIS A 1408: 2001
Delamination	Non-delamination	-
Screwing Resistance (Level)	Unbreakable (Screwing shooting)	-
Thermal Conductivity	0.166 W/mk	-

DURftex[®] **deco plus**

Decorative panels used for ceilings

CHARACTERISTICS	VALUE
Thickness	3mm, 4mm, 6mm


SUPERCLEAN



EXPOSED CEILING FRAME

(VT TOPLINE® PLUS & DURAFLEX® DECO PLUS)

VT TopLine® Plus for exposed ceiling frames is made of high-quality steel materials, and features an innovative and improved mounting head to make the system stronger. With Duraflex® Deco Plus and VT TopLine® Plus, construction works are durable and investment costs can be optimized.





Saint-Gobain Singapore Pte Ltd
2 Venture Drive
#13-18
Vision Exchange
Singapore 608526

Tel: +65 6330 8288
Fax: +65 6330 8289
eis.info@saint-gobain.com

The images provided are for reference only. Kindly obtain confirmation from DURAflex's Technical Support Personnel before submission of specification for any project. The information in this literature is accurate at the time of publishing. The publisher reserves all rights to revise the product specifications without prior notice. It is the user's responsibility to ensure that the information communicated here is current before use and that the information provided here is for guidance only. Users must ensure that they are fully conversant with the products and systems before specification or installation.

Version: DURAflex® Deco Plus_1222

