

# Weberfloor PUC MFAS

(formerly Weberfloor PUR MFAS)

Self-smoothing, ESD polyurethane screed (3-4 mm)

Weberfloor PUC MFAS is a self-smoothing, thermal shock, ESD (anti-static), polyurethane floor coating. Weberfloor PUC MFAS is matte, seamless, conductive, with heat and slip resistance.



## PRODUCT BENEFITS



CONDUCTIVE



POLYURETHANE  
 BASED



SELF  
 SMOOTHING

## USES

Weberfloor PUC MFAS is for high-tech manufacturing which requires conductive flooring, and in GMP, hygienic applications subjected to moderate traffic, impact, and surface requirements without the risk of static buildup. Used for military arsenals, high power station, explosion risk plant, clean room, warehouse, automotive plant, electronic plant and labs.

## ADVANTAGES

- Eliminate electrostatic discharge
- High mechanical and impact resistance
- Excellent abrasion and chemical resistance
- Resist fungi, mildew and bacteria growth

## TECHNICAL DATA & PHYSICAL PROPERTIES

Pot life (working time) 20 mins (15°C); 18 mins (25°C); 16 mins (30°C)  
 Recoating time (28°C) within 18 to 24 hours  
 Curing Time

	15°C	25°C	32°C
Foot Traffic	36 hours	30 hours	24 hours
Light Traffic	48 hours	36 hours	30 hours
Full chemicals cure	7 days	6 days	5 days

Density (28°C) 1.8 g/ml  
 Tensile Strength 25 MPa  
 Flexural Strength 21 N/mm<sup>2</sup>  
 Compressive Strength 50 N/mm<sup>2</sup>  
 Static Modulus of Elasticity 9400 - 9800 N/mm<sup>2</sup>  
 Adhesive Strength > 2.0 MPa (Concrete failure)  
 Service Temperature 5 to 80 °C (3mm)  
 Shore D Hardness 79 ~ 84  
 Cytotoxicity below < 0.5  
 Taber Abraser 38 mg  
 (ASTM D 4060-10)  
 Growth of Aquatic Microorganisms <2.39 or less  
 (BS 6920: Part 1: 2000 Clause 6)  
 Water Vapour Transmission ± 1.23 g/hr.m<sup>2</sup>  
 (ASTM E96/E96M-10)  
 Body Voltage (HBM) < 100 volts  
 (ANSI/ESD S20.20-2007)

**SAINT-GOBAIN (SINGAPORE) PTE LTD**  
 2 Venture Drive, #13-18,  
 Vision Exchange, Singapore 608526

(65) 63308288 (65) 63308289

eis.info@saint-gobain.com www.saint-gobain.sg

**SAINT-GOBAIN WEBER (M) SDN BHD**  
 No 29 & 31, Jalan TIAJ 2/1, Taman Industri Alam Jaya,  
 42300 Bandar Puncak Alam, Selangor D E, Malaysia

(603) 60389498/97/89 (603) 6038 9507

info.webermalaysia@saint-gobain.com www.saint-gobain.my

# Weberfloor PUC MFAS

(formerly Weberfloor PUR MFAS)

Self-smoothing, ESD polyurethane screed (3-4 mm)

## TECHNICAL DATA & PHYSICAL PROPERTIES

System Resistance (ANSI/ESD S20.20-2007) < 3.5 E + 10<sup>7</sup> ohm

ESD Floor Main Checking Criteria & Specification:

### CONDUCTIVE (with Weberprim WBAS) - BS 2050

Surface to Ground (Earth) Rg Spec	1E+4 Ω ~ 9E+6 Ω (1 x 10 <sup>4</sup> ohm to 9 x 10 <sup>6</sup> ohm)
Surface to Surface (Earth) Rs Spec	1E+4 Ω ~ 9E+6 Ω (1 x 10 <sup>4</sup> ohm to 9 x 10 <sup>6</sup> ohm)

### DISSIPATIVE (without Weberprim WBAS) - BS 2050

Surface to Ground (Earth) Rg Spec	1E+6 Ω ~ 9E+9 Ω (1 x 10 <sup>6</sup> ohm to 9 x 10 <sup>9</sup> ohm)
Surface to Surface (Earth) Rs Spec	1E+6 Ω ~ 9E+9 Ω (1 x 10 <sup>6</sup> ohm to 9 x 10 <sup>9</sup> ohm)

Specifications are subject to change without notification. Results shown are typical but reflect laboratory test procedures conducted in laboratory conditions. Actual field performance will depend on installation methods and site conditions.

## PROCEDURE & APPLICATION



### Surface Preparation

All surfaces must be clean, sound, and free from any laitance, oil, grease, and any contaminants. The concrete substrate must be dry and free from groundwater pressure with a compressive strength of  $\geq 25 \text{ N/mm}^2$  and bond strength of  $\geq 1.5 \text{ N/mm}^2$ . If the moisture content  $> 4\%$ , apply epoxy mortar ( $>80 \text{ MPa}$ ) at 4-5 mm as a moisture barrier. The concrete surface must be vacuum shot-blast or mechanical grind. Cracks and hollows should be properly remedied. Prepare grooves 3 mm wide x 3 mm deep at all edges, bay joints columns, doorways and drains for anchoring purposes.



### Mixing

	Part A	Part B	Conductive Filler	Plain Filler	Colour Paste
Weight	3 kg	3 kg	0.2 kg	10.6 kg	0.2 kg
Shelf Life	9 months	9 months	18 months	9 months	18 months

  

	Part A	Part B	Conductive Filler	Plain Filler	Colour Paste
Weight	3 kg	3 kg	0.2 kg	10.3 kg	0.5 kg
Shelf Life	9 months	9 months	18 months	9 months	18 months

Shake Part A and Part B before adding it to a clean mixing barrel. Pour all of Part A into the mixing barrel and immediately add Conductive Filler and mix for 10 - 15 seconds using a suitable electrical mixer (750 watt high power). Then, add Part B and mix for 5 seconds. Then, add Plain Filler, mix for approximately 5 seconds followed by adding Colour Paste and mix for at least 40-50 seconds until the mixture becomes homogeneous.

SAINT-GOBAIN (SINGAPORE) PTE LTD

2 Venture Drive, #13-18,  
Vision Exchange, Singapore 608526

(65) 63308288 (65) 63308289

eis.info@saint-gobain.com www.saint-gobain.sg

SAINT-GOBAIN WEBER (M) SDN BHD

No 29 & 31, Jalan TIAJ 2/1, Taman Industri Alam Jaya,  
42300 Bandar Puncak Alam, Selangor D E, Malaysia

(603) 60389498/97/89 (603) 6038 9507

info.webermalaysia@saint-gobain.com www.saint-gobain.my

# Weberfloor PUC MFAS

(formerly Weberfloor PUR MFAS)

Self-smoothing, ESD polyurethane screed (3-4 mm)

## PROCEDURE & APPLICATION



### Application

Apply Weberprim WBAS (+/- 100  $\mu$ ) as a conductive carbon layer. After Weberprim WBAS is cured (within 14-24 hours), then layer Weberfloor PUC MFAS on top of Weberprim WBAS. Apply Weberfloor PUC MFAS within the pot life, spread the composite matrix with a notched squeegee or pin rake, and set it to the correct depth or required thickness. Immediately release the air or bubble by using a spike roller.



### Care & Maintenance

Regular cleaning and maintenance will prolong the life of Weberfloor PUC MFAS. Regular cleaning using a single or double-headed rotary scrubber with an alkaline detergent is recommended.

## CONSUMPTION

Approx. 1.8 kg/m<sup>2</sup> per 1 mm coat application. Application can be up to 3-4 mm.

## COLOURS

- Standard - Grey, Light Grey, Cream, Buff, Red, Traffic Grey
- Premium - Brilliant Blue, Orange Brown, Sky Blue, Green

Colour may change on exposure to UV.

## PRECAUTION

Do not apply when the relative humidity exceeds 90% or when the surface temperature to be coated is <5% above the dew point. Do not apply when temperatures are <5°C and >40°C.

## STORAGE & PACKING

Weberfloor PUC MFAS is available in 16 kg sets. Please refer to tables for the breakdown. Shelf life as stated if unopened, and kept in dry and cool conditions.

## HEALTH & SAFETY

Good ventilation is required, if not, a portable exhaust fan shall be used. Wear protective clothing, gloves, and goggles during mixing and application process. Handle with care and in the event of eyes and skin contact, wash with plenty of water, and seek medical attention if irritation persists. Please keep out of reach of children.

\*Note: Because it is not possible to give specific instructions for the various site conditions or to control the applications, the information on this Technical Data Sheet is for general guidance only. Saint-Gobain (Singapore) Pte Ltd reserves the rights to amend the contents of the data sheet at its sole discretion. (Jan '26)

### SAINT-GOBAIN (SINGAPORE) PTE LTD

2 Venture Drive, #13-18,  
Vision Exchange, Singapore 608526

(65) 63308288 (65) 63308289

eis.info@saint-gobain.com www.saint-gobain.sg

### SAINT-GOBAIN WEBER (M) SDN BHD

No 29 & 31, Jalan TIAJ 2/1, Taman Industri Alam Jaya,  
42300 Bandar Puncak Alam, Selangor D E, Malaysia

(603) 60389498/97/89 (603) 6038 9507

info.webermalaysia@saint-gobain.com www.saint-gobain.my

bizSAFE<sub>3</sub>

